INNT	Tel.82-52-22 OVERSEAS Tel.82-52-22 SEOUL OF	gil Ungchon-myeon Ulju-gun Ulsan Korea 18-7500 Fax.82-52-268-5578 DIRECT 18-7563 Fax.82-52-228-7530 FICE	NON-ASBESTOS GASKET
		packing coupling with the latest technology	Type ' KN 11 '
Product Referenc			
Product Relefence	K/# KN 11		
Description :			
	The main components are Synthetic fibers with Neoprene binder to form non-asbestos joint sheet gasket.		
Service :			
	Maximum recommended Temperature : 370° C Maximum recommended Pressure : 100 kg _f /cm ²		
Applications			
	Water & Oil mild acids and alka Utility Services.	alis	
Construction :	SILD INN⊙	Synthetic fibers +	Neoprene binder
Gasket Design D	ata : Standard ASME S		Min. Design Sealing Stress " y
	Thickness 1.5t, 2.0t	Gasket Factor " m " 2.75	3,700 psi
	3.0t	2	1,600 psi
<u>Availability</u> :	Max.	1500mm (Non-seam) 5000mm (seam) , 2.0mm , 3.0mm , etc.	
<u>Remark :</u>		I flange surface finish for INNOSIL	cturer, and it is changed frequently. D KN 11 gasket is from 125~500AARH ation For The Top of The Technology